


Bronze Angle

Architectural Bronze Extruded Angle, Square Corners



- UNS Designation Number: UNS C38500
- Nominal Chemicals: Copper 57.00%, Zinc 40.00%, Lead 3.00%, Iron .030%
- Average Physical Properties: Tensile 60,000 psi, Yield 20,000 psi, Elongation 30%
- Specifications: ASTM B 455, Temper H50 (Extruded and Drawn)
- Stocked in 12 foot lengths

Leg (A)	Leg (B)	Thickness (C)	Lbs/Ft	Lbs/Length	Part Number
$\frac{1}{2}$	$\frac{1}{2}$	$\frac{1}{16}$.216	2.59	206868
$\frac{1}{2}$	$\frac{1}{2}$	$\frac{1}{8}$.420	5.04	206957
$\frac{3}{4}$	$\frac{3}{4}$	$\frac{1}{16}$.330	3.96	206892
$\frac{3}{4}$	$\frac{3}{4}$	$\frac{1}{8}$.640	7.68	206981
1	1	$\frac{1}{16}$.440	5.28	206923
1	1	$\frac{1}{8}$.880	10.56	207018
1	1	$\frac{1}{4}$	1.60	19.20	207131
$1 \frac{1}{4}$	$1 \frac{1}{4}$	$\frac{1}{8}$	1.09	13.08	207042
$1 \frac{1}{2}$	$1 \frac{1}{2}$	$\frac{1}{8}$	1.31	15.72	207076
$1 \frac{1}{2}$	$1 \frac{1}{2}$	$\frac{3}{16}$	1.92	23.04	207107
2	2	$\frac{1}{8}$	1.74	20.88	207254
2	2	$\frac{1}{4}$	3.48	41.76	207199
3	3	$\frac{1}{4}$	5.08	60.96	207288

Dimensions are in inches. All weights are approximate.
 Sizes not shown may be available upon request.